

L-PBF PROCESS

Layer thickness	30 µm
Hatch distance	60 µm
Laser power	200 W
Scanning speed	700 mm/s
Theoretical build-up rate	4,5 cm ³ /h

POWDER MATERIAL

AZ91D is normally used to manufacture housings for the computer, communication and consumer electronics industry and various products for lightweight construction in the aerospace and automotive industry. Therefore, AZ91D is the most commonly used magnesium die casting alloy, as AZ91D has one of the best property combinations of castability, strength and ductility. The main alloying elements are aluminum, zinc and manganese. By alloying with aluminum, an increase in strength is achieved compared to pure magnesium.

PHYSICAL PROPERTIES

Particle Size	20 µm – 63 µm
Density	1,857 g/cm ³
Thermal conductivity	65,4 W/mK
Melting range	533 °C – 680 °C
Thermal expansion	26 µm/m K

Aconity3D GmbH | Kaiserstraße 98 | 52134 Herzogenrath
 Tel.: +49 (0) 2407 55292-0 | Fax.: +49 (0) 2407 55292-99 | info@aconity3d.com

Directors: Dr. Yves Hagedorn, Hendrik Blom, Andreas Görres

VAT ID.: DE295160526 | Tax ID: 201/5940/4991
 Local Court Aachen: HRB18970


Account: 1070174691 | Routing: 39050000
 Sparkasse Aachen
 IBAN: DE66 3905 0000 1070 1746 91 | BIC: AACSD33XXX

US-Dollar Account: 107877301 | Routing: 39070024
 Deutsche Bank PGK Aachen
 IBAN: DE36 3907 0024 0107 8773 01 | BIC: DEUTDE33

CHEMICAL COMPOSITION

Element -	Mass fraction
Mg	Balance
Al	8%
Zn	0,97%
Mn	0,2%
Cr	0,0063%
S	0,0014%
Fe	0,009%
Pb	0,0035%

COMPONENT DENSITY



**Absolute Density
(Archimedes principle)** 1,82 g/cm³

**Relative Density
(Optical measurement)** 99,66%

MECHANICAL DATA

As built

Tensile strength	R _m	287,1 MPa – 297,0 MPa
Yield strength	R _{p0,2}	237,6 MPa – 255,6 MPa
Elongation at break	A	1,53% – 3,42%
Young's modulus	E	40,5 GPa – 45 GPa

All values are subject to natural volatilities depending on applied powder material, process parameters and surrounding conditions.

Aconity3D GmbH | Kaiserstraße 98 | 52134 Herzogenrath
 Tel.: +49 (0) 2407 55292-0 | Fax.: +49 (0) 2407 55292-99 | info@aconity3d.com

Directors: Dr. Yves Hagedorn, Hendrik Blom, Andreas Görres

VAT ID.: DE295160526 | Tax ID: 201/5940/4991
 Local Court Aachen: HRB18970

Account: 1070174691 | Routing: 39050000
 Sparkasse Aachen
 IBAN: DE66 3905 0000 1070 1746 91 | BIC: AACSD33XXX

US-Dollar Account: 107877301 | Routing: 39070024
 Deutsche Bank PGK Aachen
 IBAN: DE36 3907 0024 0107 8773 01 | BIC: DEUTDE33